

PTSPower, LLC - PTS INDUSTRIAL – SEE QUOTE/CONTACT US FOR PRICING INFORMATION

Lining & High Performance Comparison Chart:

PRODUCT	Working Time @ 70°F (minutes)	Recoat Time (min/max - hours)	Number of Coats	Functional Cure (hours)	Full Cure (hours)	Mix Ratio by Weight (B/A)	Mix Ratio by Volume (B/A)
<u>HPL-1110</u>	45	8 / 120	2-3	60	120	2.7:1	2:1
<u>HPL-1110-PW</u>	45	8 / 72	2-3	60	120	3.3:1	2.6:1
<u>HPL-1510</u>	45	6 / 120	1	36	120	2:1	1.8:1
<u>HPL-2131</u>	45	6 / 36	1-2	36	120	2:1	2:1
<u>HPL-2201</u>	20	3 / 24	2-3	18	120	5:1	2.7:1
<u>HPL-2221</u>	25	3 / 24	2-3	24	120	4:1	2:1
<u>HPL-2310</u>	45	8 / 72	2-3	48	120	2.6:1	2:1
<u>HPL-2510</u>	45	6 / 120	2-3	48	120	2.4:1	1.8:1
<u>HPL-2510-UW</u>	40	4 / 24	2-3	72	120	3:2	6:5
<u>HPL-3320</u>	30	6 / 48	2-3	42	120	2.1:1	3:2
<u>HPL-4300</u>	30	3 / 24	1-2	48	168	2.5:1	2:1
<u>HPL-4310</u>	45	8 / 72	2-3	72	168	3.6:1	2.6:1
<u>HPL-4320</u>	20	3 / 24	2-3	48	168	2.5:1	2:1
<u>HPL-4320-XC</u>	20	3 / 24	2-3	48	168	2.7:1	2:1
<u>HPL-4321</u>	25	3 / 24	2-3	48	168	4.7:1	3.4:1
<u>HPL-4323</u>	35	6 / 48	2-3	72	168	3:1	2:1
<u>HPL-4330</u>	30	3 / 8	1-2	48	168	2:1	2:1
<u>HPL-6310</u>	40	3 / 24	1-3	24	120	2.4:1	2.1:1